

599-12426

SUBFRAME SEMI-GLOSS BLACK

PRODUCT DESCRIPTION

Subframe Semi-gloss Black is a factory packaged colour which compliments the Dulon range. This product is ideal for use under bonnets, boots, firewalls and internal areas where a semi-gloss black finish is required. Gloss readings will be approx. 50GU @ 60°. As a 1K product, it is quick and easy to use and produces a high quality matt lacquer finish.

SUBSTRATES & PREPARATION



Subframe Semi-Gloss Black can be applied over suitably prepared:

- Original sound paint finishes except spraying enamel
- Any PPG acrylic lacquer primer




Substrates other than those stated above should be tested before use, to ensure that the performance of this product is suitable for its intended use.

PRODUCTS

Subframe Semi-Gloss Black	599-12426
Multi Midway Thinner	921-01074

MIXING RATIO



PRODUCT	PARTS
Subframe Semi-Gloss Black	1
Thinner	1 - 1.5

SPRAYGUN SETTINGS



GRAVITY	1.5 - 1.8 mm
SUCTION	1.8 - 2.0 mm

NUMBER OF COATS



2 - 3 coats

FLASH OFF (at 20°C)



2 - 3 minutes

DRYING TIMES



Air Dry at 20°C

1 - 2 hours

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

HEALTH AND SAFETY

Refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can labels.

For comprehensive Health, Safety and Environmental advice, please refer to relevant Safety Data Sheets and Product Can labels.

This product is for professional use only.

The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Drying times quoted are average times at 20°C/68°F. Film thickness, humidity and shop temperature can all affect drying times.

PPG Industries Australia Pty Ltd, 14 McNaughton Rd

Clayton, V.I.C. 3168 Australia

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

PPG Industries New Zealand Pty Ltd, 5 Vestey Dr, Mt Wellington

Auckland, New Zealand

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

Protec and the Protec Logo are registered trademarks of Protec Pty Ltd.